



MANUFACTURERS OF
ELECTRICAL INSULATION MATERIALS
 INSULATING COMPONENTS FOR
POWER SYSTEMS EQUIPMENT

TheGundCompany, Inc
 St. Louis, Missouri—USA
 TEL-314.423.5200
 FAX-314.423.9009

MATERIAL DATA SHEET

Item: H-91 Cement Fiber Board

Description: The H-91 grade of cement fiber board has a substrate of portland cement reinforced with selected non-asbestos fibers in order to offer improved compressive strength versus grade NAD-11. Grade H-91 also offers an improved temperature resistance up to a maximum temperature rating of 1400 °F. Grade H-91 can be used for a variety of applications requiring a relatively low cost dielectric that can survive high temperature applications.

		English units	SI Units
Availability:	Laminate Sheets:	Thickness: 0.188"–3"	4.78mm–76mm
		Sheet Sizes: 37"x49"	94cmx124cm
	Fabricated Parts:	The Gund Company custom fabricates insulation materials to the exact specifications and drawings of our customers.	

Key Characteristics:	Test Method	Units - English (SI)	Typical Values
Composition			Non-asbestos fiber cement
Density		lbs/in ³ (g/cc)	0.069(1.91)
Maximum Operating Temperature		°F(°C)	1,400(760)
Compressive Strength	ASTMD-695	psi(MPa)	16,675(115)
Shear Strength	ASTMD-732	psi(MPa)	3,700(26)
Flexural Strength	ASTMD-790	psi(MPa)	4,350(30)
Water Absorption	ASTMD-570	%	10
Thermal Conductivity	ASTMC-177	BTU/in/hr/ft ² °F	3.4
Arc Resistance	ASTMD-495	sec	>360
Dielectric Strength	ASTMD-149	kV/in	2
Dielectric Strength	ASTMD-149	kV	14

All of the information, suggestions, and recommendations herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty, expressed or implied, including, without limitation, warranty of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.